

CI/SfB		Yt3	
CAW Z20			
Uniclass L673			

Description

SP350 is a one component, non-sagging, elastic adhesive based on hybrid polymers.

Colour

White.

Packaging

310 ml cartridges (12 per carton)

Technical Information

Property	Test Method	Results
Specific Gravity	DIN 52451-A	1.5
Consistency	EN 27390 20 mm profile	0 mm , non-sagging
Film Formation Time		Approx. 15 min. at 23°C/50% r.h.
Cure Rate		Approx. 3.5 mm/1st day
Volume Shrinkage	DIN 52451	3.4%
Modulus at 25% Elongation	DIN 53504 S2	0.8 N/mm ²
Modulus at 100% Elongation	DIN 53504 S2	1.5 N/mm ²
Tensile Strength	DIN 53504 S2	Approx. 3.0 N/mm ²
Elongation at Break	DIN 53504 S2	Approx. 470 %
Module at 100 % Elongation	DIN EN ISO 8339 Method A	Approx. 1.3 N/mm ²
Tensile Strength	DIN EN ISO 8339 Method A	Approx. 2.0 N/mm ²
Elongation at Break	DIN EN ISO 8339 Method A	Approx. 350%
Recovery	DIN EN ISO 7389 Method B	60%
Shore A Hardness	DIN 53505	55°
Application Temperature		+5°C up to +40°C
Service Temperature		-40°C up to + 90°C
Storage		Store in shaded dry conditions between +5°C and +25°C.
Shelf Life		12 months when stored as recommended in original unopened containers.

Necessary Tools

- Standard cartridge skeleton gun and a sharp knife to cut nozzle.

Preparation

- Always carry out a test to confirm compatibility prior to use.
- Surfaces to be bonded must be clean, dry, dust-proof and degreased.
- Roughen non-porous surfaces.
- On materials such as glass, aluminium, ceramics, lacquered wood, epoxy and polyester no primer is required. For other materials, please contact tremco illbruck Technical Services.



SP350

Fix & Seal High Tack



Usage / Purpose

SP350 has been developed to bond materials to floor, wall and ceiling, where the extremely high initial strength of the product is very useful for this high performance adhesive.

Key Benefits

- High initial grab and rapid development of final bond
- Formulation is solvent free, very low odour, and chemically neutral
- Instant grab can minimise the need for additional clamping or other mechanical supports
- Good resistance to light, weather and ageing - suitable for internal and external applications

Fix & Seal High Tack

Application

- Ensure good contact between the joint surfaces before applying adhesive. Apply a bead of adhesive to one or both surfaces. For larger bond areas, apply parallel beads at approx. 100 mm spacing, so that after joining the parts an aerated gap remains between the beads.
- Bring the two components together immediately. Sufficient working strength will normally develop after 10 minutes.

Coverage

Width	Depth
5 x 5	12.4
8 x 6	6.4
10 x 8	3.8
15 x 10	2.0
20 x 12	1.2
25 x 15	0.8
30 x 15	0.6

Cleaning

Remove excess adhesive immediately with AT200 High Strength Cleaner. Ensure surface is solvent resistant before cleaning. Cured adhesive can only be removed mechanically.

Please Note

Not suitable for bonding polyethylene, polypropylene, Teflon® or nylon. Not recommended for sheet laminate. Do not use as a structural glazing adhesive. Not suitable for use as a for bonding of plastics that are sensitive to stress cracking. Not recommended for prolonged exposure to water. Contact with bituminous or tar containing surfaces can lead to discolouration. Staining on natural stone may occur. If 2 non-porous substrates are glued the maximum width should not exceed 15 mm.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco

illbruck written instructions and (b) in any application recommended by Tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



tremco illbruck Limited
Coupland Road, Hindley Green
WN2 4HT Wigan
United Kingdom
T: +44 1942 251400
F: +44 1942 251410

info.uk@tremco-illbruck.com
www.tremco-illbruck.co.uk