

Product Data

High Tear Strength Silicone Rubber Compound TSE260 series

TSE260 series is a high tear strength peroxide cured silicone rubber compound for molding.

KEY FEATURES

- ◆ Excellent tear strength
- ◆ Translucent

APPLICATIONS

Extremely tear resistant parts:

- ◆ Diaphragms
- ◆ O-rings
- ◆ Gaskets
- ◆ Boots
- ◆ Baby bottle nipples

TYPICAL PROPERTY DATA

(JIS K 6249)

PROPERTIES	TSE260-3U	TSE260-5U	TSE260-7U
UNCURED PROPERTIES			
Appearance	Translucent	Milky white, Translucent	
Williams plasticity	160	210	320
CURED PROPERTIES (Press cure 10min @170°C; Post cure 4h @ 200°C)			
TC-8 curing agent %	0.3	0.3	0.6
MECHANICAL PROPERTIES			
Density (23°C) g/cm ³	1.09	1.13	1.18
Hardness (Type A)	30	55	70
Tensile strength MPa {kgf/cm ² }	10.0 {102}	11.4 {116}	11.5 {117}
Elongation %	900	680	540
Tear strength (Crescent) N/mm {kgf/cm}	32 {33}	33 {34}	34 {35}
Linear shrinkage %	4.1	4.4	4.3
Compression set* %	28	24	26
ELECTRICAL PROPERTIES			
Volume resistivity MΩ·m	3.0×10 ⁸	3.0×10 ⁸	3.0×10 ⁸
Dielectric strength kV/mm	28	30	27
HEAT RESISTANCE (72h @ 200°C)			
Hardness change	+1	+9	+6
Tensile strength change %	-36	-21	-21
Elongation change %	-32	-45	-43

*: 180°C, 22h

Typical property data values should not be used as specifications.

HANDLING AND SAFETY

- ◆ Wear eye protection and protective gloves when handling this product.
- ◆ Cure only where appropriate ventilation systems exist.

STORAGE

- ◆ Store in a cool and dry place out of direct sunlight.
- ◆ Keep out of the reach of children.

PACKAGING

20kg box

Issued Feb. 2000/2nd revised Dec. 2003, TSE260 series E

FOR INDUSTRIAL USE ONLY

It is the responsibility of the user to determine the suitability of any Momentive Performance Materials Japan product for any intended application. NEVER USE ANY MOMENTIVE PERFORMANCE MATERIALS JAPAN PRODUCT FOR IMPLANTATION OR INJECTION INTO THE HUMAN BODY. Specifications are available by contacting Momentive Performance Materials Japan. Typical property data values should not be used as specifications. Inasmuch as Momentive Performance Materials Japan LLC has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the suitability of the material for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Momentive Performance Materials Japan patent covering use or as recommendations for use of such materials in the infringement of any patent. Material Safety Data Sheets are available upon request from Momentive Performance Materials Japan. The contents of this catalog are subject to change without notice. No part of this data may be reproduced without the prior approval of Momentive Performance Materials Japan.



Momentive Performance Materials Japan LLC

<http://www.momentive.com>

Technical Answer Center (Japan): Phone: +81-276-20-6182 FAX: +81-276-31-6259
Tokyo Head Office: Phone: +81-3-5544-3111 FAX: +81-3-5544-3122